



PolyLinemarking

2K polyurethane for line marking

6300 - line

Description

- 2-pack polyurethane high durability linemarking coating

Properties

- Excellent abrasion and wear resistance
- Suitable over epoxy and polyurethane floor coatings
- Fast dust-free time

Typical Applications

- Commercial car parks
- Factory and warehouse floors
- Retail complex floors
- **This is an industrial grade product and is not recommended for use in domestic situations**

General Data

- Weather resistance Recommended for both interior exterior usage
- Solvent resistance Resists splashes of most common solvents; not recommended for continuous immersion
- Chemical resistance Good
- Abrasion resistance Excellent
- Suitable substrates Rhinofloor[®] HS and SF Premium, Rhiname[®], Polycoat 121, 221 and 321

Specifications (at 25°C and 50% relative humidity)

- Resin type..... Polyester Polyurethane
- Mixing ratio..... 2 : 1 (by volume)
- Solids content..... 5 - 55% (by volume - Colour dependent)
- Typical film thickness (per coat)..... 30 - 40 microns (dry)
60 - 80 microns (wet)
- Theoretical coverage..... 10 - 14m² / L @ 30 microns dry film thickness (dependant on colour)
- Touch dry..... 30 minutes
- Tack free..... 3 hours
- Hard dry..... 16 hours
- Full cure..... 7 days
- Recoating..... within 6 to 18 hours to ensure good intercoat adhesion
after 24 hours, sanding is required before recoating
- Pot life..... 2 hours (depending on temperature and level of thinner added)
- Gloss..... Satin
- Colour..... Range of standard colours – (Subject to minimum order requirement)
- Shelf life..... minimum 12 months (in cool, dry conditions with unopened containers)

PolyLinemarking

Surface Preparation

- Apply as soon as possible to freshly laid Epoxy or Polyurethane floor coating (within 12-24 hours of application)
- Beyond these times, light sanding will be necessary to ensure good intercoat adhesion
- Not suitable for application directly to bare concrete. Refer to recommendations in General Data above

Mixing recommendation

- Mix only the quantity required for the job
- Mix Pack A with Pack B in the ratio 2:1 (by volume)
- Stir thoroughly with a broad paddle or low-speed mechanical mixer (350 RPM) to ensure even mixing
- Thinning is not normally required. Thin with Wagon Paints T1 PU Spray Thinner if necessary.

Application

- May be spray applied using airless or conventional air spray equipment
- Small areas may be coated by brush or roller
- Product must be applied at even film build to avoid gloss variations
- **Airless Spray** nozzle size.....0.33 - 0.38 mm
nozzle pressure.....2800 - 4000 psi (19 - 27mPa)
volume of thinner.....RFU
- **Air Spray** nozzle size.....1.6 - 2.0 mm
nozzle pressure.....45 - 60 psi (300 - 400kPa)
volume of thinner..... RFU
- **Cleaning solvent**T1 PU Spray Thinner

Caution: Store PolyLinemarking Pack A & B in a cool, dry location. Do not allow water to contaminate the products. Atmospheric moisture will cause the Part B to solidify in the can if allowed excessive contact with air. Part full containers have limited storage stability. Must not be applied over damp surfaces. Do not apply when the air/surface temperatures are below, or are likely to fall below, 10°C or the relative humidity is above 70%.

Maintenance

- The service life of a floor will be considerably extended if good housekeeping practices are followed. Regular cleaning of "Polylinemarking" can be carried out using a mop, brush, or automatic rotary buffing / scrubbing machine, in unison with a mild alkaline detergent. Please refer Wagon Paints technical department for further information.

Safety precautions

- **Refer to the relevant Material Safety Data Sheets for Pack A and Pack B**
- Contents are flammable – keep away from all ignition sources
- Avoid contact with skin and eyes – when mixing, wear gloves and goggles
- When spraying, ensure adequate ventilation and wear appropriate protective clothing and equipment

Pack A **Packaging Group II** **UN No. 1263**
Pack B **Packaging Group II** **UN No. 1866**

PolyLinemarking

Pack sizes

Pack size	6 litre kit	15 litre kit	30 litre kit
Pack A	4 litre	10 litre	20 litre
Pack B	2 litre	5 litre	10 litre

Anti-slip Characteristics

If specification / contract document states that a floor must conform to a particular Australian Standard for slip resistance, then an aggregate must be added into the Rhinofloor flooring system to impart the required non-slip rating.

Please refer to Wagon Paints technical department for further information.

This product must be applied by an applicator approved by Wagon Paints. For a list of approved applicators, please contact:

Mr. Cameron O'Donnell
Technical Representative – Flooring Products

Mob **0411 557 234**
B/H (03) 9729 1344
Email codonnell@wagonpaints.com.au

The 'Rhinofloor' floor-coating range has been designed / manufactured primarily to protect the concrete substrate. Please be aware that scratching, marring, colour-fading, gloss reduction, etc, will be evident, with the rate of film attack directly related to service conditions within the areas that these coatings have been applied. Wagon Paints, incorporating Rhino Coatings, take no responsibility for film attack as mentioned, as these issues are a known fact inherent to all industrial epoxy and polyurethane floor coatings.

Authorised: A. De Mello, Sales Manager

June 2008

These technical data and recommendations are based on tests and information believed to be accurate at the time of printing. They should not be construed as containing any warranty, either expressed or implied. Users should conduct their own tests to determine final suitability of this product.



Wagon Paints

5 Stephenson Road, Bayswater North, Victoria 3153 Australia
Phone: 61 3 97291344 Fax: 61 3 97202179 Email: sales@wagonpaints.com.au