



Rhinofix™

Industrial epoxy bonding agent

7350 - line

Description

- 2-pack epoxy / polyamide adhesive, filler and encapsulating resin

Properties

- High bond strength
- Waterproof
- Low shrinkage

Typical Applications

- Timber adhesive for boat building
- Filler for concrete floors
- Sheathing of timber, with glass fibre

General Data

- | | |
|-----------------------|--|
| ▪ Weather resistance | Good (will chalk and yellow on prolonged exterior exposure, however film integrity is not compromised) |
| ▪ Solvent resistance | Fair |
| ▪ Chemical resistance | Fats & Oils Excellent |
| | Alkalis, dilute Excellent |
| | Acids, dilute Good |
| ▪ Abrasion resistance | Very good |

Specifications (at 25°C and 50% relative humidity)

- Resin type.....Epoxy / polyamide
- Mixing ratio.....3 : 1 (by volume)
- Solids content..... 100% (by volume)
- Typical film thickness (per coat)..... not applicable
- Clamping time..... 8 hours
- Full cure..... 7 days (will not cure at temperatures below 10°C)
- Pot life..... 30 – 60 minutes (depending on temperature and size of mix)
- Colour..... Clear; honey-like colour and consistency
- Shelf life..... minimum 12 months (in cool, dry conditions)

Surface Preparation

- **Steel** surfaces must be degreased, then subjected to abrasive blasting (to AS 1627.4 Class 2½) or abrasion with a suitable power cleaning tool (e.g. disc sander).
- **Concrete** must be cured for a minimum of 28 days. Remove all traces of curing membrane, release agents, oil and grease. Acid etch with a 10% solution of Phosphoric Acid or Hydrochloric Acid in water, or shotblast. Allow concrete to dry thoroughly before applying Rhinofix - moisture content of concrete to be no greater than 5.5%.
- **Timber** Sand wood with medium paper and dust off. Be sure wood is clean and dry. (Moisture content not higher than 8-10%)
- **Fibreglass** Coarsely abrade surface with a disc sander

Rhinofix™

Mixing recommendation

- Mix only the quantity required for the job
- Mix Pack A with Pack B in the ratio 3:1 (by volume)
- Stir thoroughly with a broad paddle or low-speed mechanical mixer (350 RPM) to ensure even mixing
- Kiln dried sand / fillers can be added to 'bulk-out' resin product

Application

- May be applied using brush or trowel
- May be thickened with Epoxy Thickener if applying to vertical surfaces
- **No. of Coats**.....One
- **Cleaning solvent** 3 Epoxy Thinner

Safety precautions

- **Refer to the relevant Material Safety Data Sheets for Pack A and Pack B**
- Avoid contact with skin and eyes – when mixing, wear gloves and goggles

Pack A	Packaging Group N/A	UN No. N/A
Pack B	Packaging Group III	UN No. 2735

Pack sizes

Pack size	1 litre kit	4 litre kit	20 litre kit
Pack A	0.75 litre	3 litre	15 litre
Pack B	0.25 litre	1 litre	5 litre

The 'Rhino floor' floor-coating range has been designed / manufactured primarily to protect the concrete substrate. Please be aware that scratching, marring, colour-fading, gloss reduction, etc, will be evident, with the rate of film attack directly related to service conditions within the areas that these coatings have been applied. Wagon Paints, incorporating Rhino Coatings, take no responsibility for film attack as mentioned, as these issues are a known fact inherent to all industrial epoxy and polyurethane floor coatings.

Authorised: A. De Mello, Sales Manager

June 2008

These technical data and recommendations are based on tests and information believed to be accurate at the time of printing. They should not be construed as containing any warranty, either expressed or implied. Users should conduct their own tests to determine final suitability of this product.



Wagon Paints

5 Stephenson Road, Bayswater North, Victoria 3153 Australia
Phone: 61 3 97291344 Fax: 61 3 97202179 Email: sales@wagonpaints.com.au