



Rhinothane[®] AC

2K acrylic polyurethane finish coat

6050 - line

Description

- 2-pack acrylic-modified polyurethane high performance topcoat

Properties

- Superior weather resistance and light fastness
- Easily recoatable
- Excellent gloss retention
- Fast dust-free time

Typical Applications

- Steel fabrications (e.g. electrical transformers)
- Truck and bus refinishing

General Data

- | | |
|-----------------------|--|
| ▪ Weather resistance | Excellent |
| ▪ Solvent resistance | Resists splashes of most common solvents; not recommended for continuous immersion |
| ▪ Chemical resistance | Good |
| ▪ Abrasion resistance | Good |
| ▪ Suitable primers | Rhinamel [®] CC Primer, Rhinogrip [®] Etch Primer, Epoxycoat |

Specifications (at 25°C and 50% relative humidity)

- | | |
|--|--|
| ▪ Resin type..... | Acrylic-modified polyurethane |
| ▪ Mixing ratio..... | 4 : 1 |
| ▪ Solids content..... | 40% (by volume) |
| ▪ Typical film thickness (per coat)..... | 25 microns (dry)
65 microns (wet) |
| ▪ Theoretical coverage..... | 15m ² / L @ 25 microns dry film thickness (dependant on colour) |
| ▪ Touch dry..... | 30 - 45 minutes |
| ▪ Hard dry..... | 12 hours |
| ▪ Full cure..... | 7 days |
| ▪ Recoating..... | after 16 hours |
| ▪ Pot life..... | 4 hours (depending on temperature and level of thinner added) |
| ▪ Gloss..... | Gloss |
| ▪ Colour..... | Extensive colour library and easy colour matching with Coloryte [®]
Industrial Tint System |
| ▪ Shelf life..... | minimum 12 months (in cool, dry conditions; unopened containers) |

Surface Preparation

- Bare steel surfaces must be degreased, then subjected to abrasive blasting (to AS 1627.4 Class 2½) or abrasion with a suitable power cleaning tool (e.g. disc sander)
- Not suitable for application directly to bare metal. Refer to recommendations Coatings Systems below.

Mixing recommendation

- Mix only the quantity required for the job
- Mix Pack A with Pack B in the ratio 4:1
- Stir thoroughly with a broad paddle or mechanical mixer to ensure even mixing of the two parts
- Thin up to 20% by volume with Wagon Paints' T1 PU Spray Thinner (see Application directions), and stir as above

Rhinothane® AC

Application

- May be spray applied using airless or conventional air spray equipment
- Small areas may be coated by brush or roller
- **Airless Spray** nozzle size.....0.33 - 0.38 mm
nozzle pressure.....2800 - 4000 psi (19 - 27mPa)
volume of thinner.....up to 10%
- **Air Spray** nozzle size.....1.6 - 2.0 mm
nozzle pressure.....45 - 60 psi (300 - 400kPa)
volume of thinner..... up to 20%
- **Cleaning solvent** T1 PU Spray Thinner

Coating Systems

Substrate	Primer	Undercoat*	Topcoat
Aluminium	Rhinogrip® Etch		Rhinothane® AC
Galvanised Iron	Rhinogrip® Etch	Rhinamel® CC Primer	Rhinothane® AC
Steel	Rhinogrip® Etch	Rhinamel® CC Primer	Rhinothane® AC
Zincseal / Zinalume	Rhinogrip® Etch		Rhinothane® AC
Fibreglass		Rhinamel® CC Primer	Rhinothane® AC
Timber		Rhinamel® CC Primer	Rhinothane® AC

Rhinogrip Etch primer may be directly overcoated with Rhinothane® AC to provide an economical and quick drying alternative to the traditional two pack epoxy undercoats. For optimum performance in severe environments, the use of a single coat of epoxy undercoat between the Rhinogrip® Etch & Rhinothane® AC is recommended.

*Epoxycoat may be used in place of Rhinamel® CC Primer

Caution:

Store Rhinothane® AC Pack A & B in a cool, dry location. Do not allow water to contaminate the products.

Must not be applied over damp surfaces. Do not apply when the air/surface temperatures are below, or are likely to fall below, 10°C or the relative humidity is above 70%.

Safety precautions

- **Refer to the relevant Material Safety Data Sheets for Pack A and Pack B**
- Contents are flammable – keep away from all ignition sources
- Avoid contact with skin and eyes – when mixing, wear gloves and goggles
- When spraying, ensure adequate ventilation and wear appropriate protective clothing and equipment

Packaging Group II **UN No.** 1263 (Pack A); 1866 (Pack B)

Pack sizes 4 litre, 20 litre (Pack A)
1 litre, 5 litre (Pack B)

Authorised: A. De Mello, Sales Manager

June 2008

These technical data and recommendations are based on tests and information believed to be accurate at the time of printing. They should not be construed as containing any warranty, either expressed or implied. Users should conduct their own tests to determine final suitability of this product.



Wagon Paints

5 Stephenson Road, Bayswater North, Victoria 3153 Australia
Phone: 61 3 97291344 Fax: 61 3 97202179 Email: sales@wagonpaints.com.au