



T19 Electrostatic No. 2 Thinner

Code: THT190000

Description

- Thinner for adjusting resistivity and spray viscosity of enamel primers and topcoats

Properties

- Adjusts resistivity of coatings for use with electrostatic spray equipment
- Improves "wrap" on tubular or complex steel fabrications

Typical Applications

- Used in Zinc Phosphate Primer and other alkyd-based anticorrosive primers
- Used in Rapid Enamel and other alkyd-based topcoats

General Data

- Specially formulated blend of hydrocarbon and polar chemical solvents

Specifications (at 25°C and 50% relative humidity)

- Appearance.....Low viscosity, clear, water-white liquid
- Specific Gravity.....0.8
- Boiling Range..... 80 - 130°C

Mixing recommendation

- Add up to 30% by volume to achieve required resistivity reading
- Capable of adjusting resistivity down to 1 - 2 MΩ

Safety precautions

- **Refer to the relevant Material Safety Data Sheet**
- Contents are flammable – keep away from all ignition sources
- Avoid contact with skin and eyes – when mixing, wear gloves and goggles
- When spraying, ensure adequate ventilation and wear appropriate protective clothing and equipment

Packaging Group II UN No. 1263

Pack sizes 4 litre, 20 litre

Authorised: A. De Mello, Sales Manager

June 2008

These technical data and recommendations are based on tests and information believed to be accurate at the time of printing. They should not be construed as containing any warranty, either expressed or implied. Users should conduct their own tests to determine final suitability of this product.



Wagon Paints

**5 Stephenson Road, Bayswater North, Victoria 3153 Australia
Phone: 61 3 97291344 Fax: 61 3 97202179 Email: sales@wagonpaints.com.au**