



T6.03 Epoxy Thinner

Description

- Blended thinner for reducing 2K epoxy coatings to spray viscosity

Properties

- Fast initial flash-off for improved vertical hold up
- Greater penetration into surfaces when added to first coat

Typical Applications

- Thinning of epoxy products[®] for spray application (and first coat of roller application)

General Data

- Specially formulated blend of hydrocarbon and chemical solvents

Specifications (at 25°C and 50% relative humidity)

- Appearance..... Low viscosity, clear, water-white liquid
- Specific Gravity..... 0.85
- Boiling Range..... 80 - 143°C

Mixing recommendation

- spray 0- 5% by volume on mixed Pack A and Pack B
- brush/roller 0-10% by volume on mixed Pack A and Pack B
- application of 1st coat to concrete 20 - 25% by volume on mixed Pack A and Pack B

Safety precautions

- **Refer to the relevant Material Safety Data Sheet**
- Contents are flammable – keep away from all ignition sources
- Avoid contact with skin and eyes – when mixing, wear gloves and goggles
- When spraying, ensure adequate ventilation and wear appropriate protective clothing and equipment

Packaging Group II **UN No. 1263**

Pack sizes 1 litre, 4 litre, 20 litre

Authorised: A. De Mello, Sales Manager

Sep 2015

These technical data and recommendations are based on tests and information believed to be accurate at the time of printing. They should not be construed as containing any warranty, either expressed or implied. Users should conduct their own tests to determine final suitability of this product.