



# Rhicryl®

Acrylic copolymer colour finish

1500 - line

## Description

- Solvent-based acrylic topcoat

## Properties

- Fast drying
- Non-yellowing film
- Resistant to water and alkaline solutions
- Controls dusting of concrete surfaces

## Typical Applications

- Coating of concrete, bricks and masonry
- Sealing concrete floors / driveways and concrete roof tiles
- The Rhicryl® product is **NOT** suitable for application to 'Terracotta' or 'Slate' roof and floor tiles

## General Data

- |                       |                                   |
|-----------------------|-----------------------------------|
| ▪ Weather resistance  | Excellent                         |
| ▪ Water resistance    | Very good                         |
| ▪ Solvent resistance  | Generally poor                    |
| ▪ Chemical resistance | Mineral fats & oils.....Very good |
|                       | Alkalis (dilute).....Excellent    |
| ▪ Abrasion resistance | Good                              |

## Specifications (at 25°C and 50% relative humidity)

- Resin type..... Acrylic copolymer
- Typical solids content..... 35 - 40% (by volume - colour dependent)
- Typical film thickness (per coat)..... 45 - 60 microns (dry)  
125 - 165 microns (wet)
- Theoretical coverage..... 6 - 8m<sup>2</sup> / L @ 45 microns dry film thickness (dependant on colour)
- Touch dry..... 30 minutes
- Hard dry..... 4 - 6 hours
- Trafficable..... Pedestrian traffic (4 - 6 hours) / Vehicular traffic (5 - 7 days)
- Recoating..... 4 - 6 hours
- Gloss..... Low to Full Gloss (Subject to: Film Thickness / Substrate Porosity)
- Colours..... Range available (Subject to minimum order requirement)
- Shelf life..... minimum 12 months (in cool, dry conditions)

# Rhicryl®

## Surface Preparation

- **New Concrete** must be cured for a minimum of 28 days. High-pressure waterblast (3000 psi) the substrate, in conjunction with a mild alkaline detergent, to remove all traces of curing membrane, release agents, oil and grease. Acid etch with a 10% solution of Phosphoric Acid or Hydrochloric Acid in water, then high-pressure waterblast (3000 psi) to remove residual acidity. (Alternatively, shotblast or diamond grind to remove surface laitance). Allow concrete to dry thoroughly before applying the Rhicryl® product. 'Acid-etching' is not a suitable preparation technique for concrete substrates suspected of being pre-treated with 'Densifier' or 'Penetrating Sealer' type products. Preparation via mechanical abrasion of the substrate must be performed prior to application (i.e. Scabbling / Shot-blasting / Diamond-grinding) to permit maximum adhesion characteristics of the system as specified. Please refer Wagon Paints Technical Department for further information.
- **Existing Concrete** must be suitably cleaned to remove traces of any substance which could affect adhesion of the Rhicryl® product. Eg. Paint, mildew mould, algae, oil and grease. (Mechanical abrasion of the substrate may be required to perform this 'cleaning' function with regard to existing coatings). High-pressure waterblast (3000 psi) the substrate, in conjunction with a mild alkaline detergent, to remove all traces of curing membrane, release agents, oil and grease. Acid etch with a 10% solution of Phosphoric Acid or Hydrochloric Acid in water, then high-pressure waterblast (3000 psi) to remove residual acidity. (Alternatively, shotblast or diamond grind to remove surface laitance, existing coatings, etc). Allow concrete to dry thoroughly before applying the Rhicryl® product. 'Acid-etching' is not a suitable preparation technique for concrete substrates suspected of being pre-treated with 'Densifier' or 'Penetrating Sealer' type products. Preparation via mechanical abrasion of the substrate must be performed prior to application (i.e. Scabbling / Shot-blasting / Diamond-grinding) to permit maximum adhesion characteristics of the system as specified. Please refer Wagon Paints Technical Department for further information.
- **Existing Coatings** This product can be applied over well-adhered aged single-pack coatings, subject to the application & verification of a test-patch by the purchaser, and with suitable High-pressure water blasting and / or mechanical preparation of the surface where necessary. Please consult Wagon Paints Technical Department for further information.
- **Moisture testing** can be performed by placing a piece of plastic over a small area, tape down the edges and leave for 1 hour. Then, remove plastic, and if there is no moisture on either surface, the concrete should be sufficiently dry for coating application.

## Mixing recommendation

- Mix the entire contents of the can before decanting
- Stir thoroughly with a broad paddle or low-speed mechanical mixer (350 RPM) to ensure even mixing
- Apply the Rhicryl® sealer as thinly as possible, as 'thicker' coats, especially applied during the warmer months, can cause bubbles to appear. If bubbling occurs, or substrate porosity is problematic, reduce with T7 thinners up to 50%. Please refer Wagon Paints Technical Department for further information.

## Application

- May be applied using roller, airless or low-pressure air spray equipment (Refer OH&S requirements)
- "Broom" application is recommended for "uneven / stenciled / impression" substrates
- Small areas may be coated by brush
- **Roller** nap size.....10 – 15 mm (Microfibre - Applicator preference)
- **Airless Spray** nozzle size.....0.33 – 0.38 mm  
nozzle pressure.....2000 – 2500 psi (14 - 17mPa)  
volume of thinner.....nil
- **Air Spray** nozzle size.....1.6 – 2.0 mm  
nozzle pressure.....45 – 60 psi (300 - 400kPa)  
volume of thinner.....0 – 10% (Using T7 Thinner)
- **No of coats**.....1 – 3 (depending on porosity of substrate)
- **Thinner / Cleaning solvent** ..... T7 Thinner

## Safety precautions

- **Refer to the relevant Safety Data Sheets (SDS)**
- Contents are flammable – keep away from all ignition sources
- Avoid contact with skin and eyes – when mixing, wear gloves and goggles
- When spraying, ensure adequate ventilation and wear appropriate protective clothing and equipment

**Packaging Group II**      **UN No. 1263**

# Rhicryl®

## Anti-slip Characteristics

If nonslip characteristics are required, please refer 'Rhicryl® Nonslip' product data sheet / Wagon Paints Technical Department for further information. The 'Rhicryl® Nonslip' product is only suitable for foot traffic, and should not be used where vehicular or hard-wheeled traffic is prevalent.

Wagon Paints Australia, incorporating Rhinofloor Coatings, does not warrant the "Anti-slip" performance of the coating system(s), with or without aggregate, as this characteristic is out of our control. It is up to the applicator / contractor / purchaser to satisfy any "Anti-slip" regulations or standards required if applied to areas which may be hazardous to pedestrian or vehicular traffic.

## Maintenance

The service life of a floor will be considerably extended if good housekeeping practices are followed. Regular cleaning of "Rhicryl®" can be carried out using a mop or brush, in unison with a mild alkaline detergent. Please refer Wagon Paints technical department for further information.

## Pack sizes

Pack size	20 litre
-----------	----------

\*Not available in quantities larger than 20lt - Refer to RHINOFLOOR Technical Representative for details

Do not mix RHICRYL® Clear with RHICRYL® pigmented products, as there may be issues with resin compatibility. Refer to Wagon Paints' Technical Department for further information.

The 'Rhinofloor' floor-coating range has been designed / manufactured primarily to protect the concrete substrate. Please be aware that scratching, marring, colour-fading, gloss reduction, etc, will be evident, with the rate of film attack directly related to service conditions within the areas that these coatings have been applied. Wagon Paints, incorporating Rhinofloor Coatings, take no responsibility for film attack as mentioned, as these issues are a known fact inherent to all industrial floor coatings.

### For all enquiries please contact:

Technical Department  
Wagon Paints Australia Pty Ltd  
(Incorporating RHINOFLOOR Coatings)  
Member of TRANSOCEAN COATINGS Group

Phone 03 9729 1344  
Email [technical@wagonpaints.com.au](mailto:technical@wagonpaints.com.au)  
Web [www.wagonpaints.com.au](http://www.wagonpaints.com.au)



Authorised: J. Skangos - Technical Manager

February 2024

These technical data and recommendations are based on tests and information believed to be accurate at the time of printing. They should not be construed as containing any warranty, either expressed or implied. Users should conduct their own tests to determine final suitability of this product.

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either the quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product, as well as the data sheet, without notice.

® Registered Trademark of Wagon Paints Australia Pty Ltd



5 Stephenson Road, Bayswater North, Victoria 3153 Australia  
Phone: 61 3 97291344 Email: [sales@wagonpaints.com.au](mailto:sales@wagonpaints.com.au)